

检测报告 Test Report

报告日期/Date: 2020/11/20

报告编号/Report No.: 2020367120

页码/Page: 1/3

委托单位/Client: 上海钦凯实业有限公司
Shanghai Qinkai Industry Co.,Ltd
地址/Address: 上海金山区朱泾镇亭枫公路2318号
样品名称/Product: 不锈钢线槽组合件Cable Trays Stainless steel
型号规格/Dimension: 400*40*1.5*300mm
送样数量/Quantity: 1set
等级/Grade: ———
材料/Material: 316L

委托人提供以上信息, 实验室不负责其真实性。

The information above is provided by the client. Our laboratory is not responsible for its authenticity.

样品来源/Sample Source: 委托方送样 Supplied by client
样品描述/Sample Description: 完好, 样品表面金属本色 Integrity, self-colored.
到样日期/Receiving Date: 2020-11-18
检验日期/Test Date: 2020-11-19

结果判定依据/Specification & Conformance Requirement:

委托方提供的技术要求

检测结果/Test Result: 参见下页See next page



扫码查真伪



微信客服

浙江国检检测技术股份有限公司
Zhejiang Guojian Testing Technology Co.,Ltd.

批准/Approved by:

声明: 1. 本报告无批准人签字或者无本实验室检验专用章无效; 2. 本报告涂改无效; 3. 本实验室仅对本报告正式文本负责, 任何复印件、传真件、影印件仅作参考; 4. 本报告各页不可分割, 部分使用无效; 5. 未经实验室书面同意不得部分复制报告; 6. 本报告检验结果仅对所检样品有效; 7. 对检验结果有异议应及时提出, 样品在本实验室的保留期限一般为45天; 8. 样品被取回或超出保留期限, 本实验室将不再提供复测; 9. 报告编号数字最后一位为版本号, 首版为“0”。报告修改后版本号递增, 原版作废。报告修改后版本号递增, 原版作废, 修改内容加粗字体标识; 10. 本报告未给出不确定度的, 判定规则为简单接受。

Declaration: 1. This test report shall be invalid if without the laboratory testing seal or signatures of authorized signatory. 2. This test report shall be invalid if altered. 3. Our laboratory is only responsible for the original report. Copying, faxing, photocopying versions of the report is only for reference purpose. 4. This report is invalid if parted. 5. This test report shall not be reproduced except in full without the written approval of the laboratory. 6. This report is responsible for designated samples only. 7. Any objection of the test result should be declared timely. The tested samples will be kept for 45 days. 8. If tested samples are returned or expired, retest will no longer be offered. 9. The last digit of the report number is the version number, the original number is "0". The version number increased when this report revised, meanwhile the original report invalid, the changed information is identified in bold font. 10. If the uncertainty is not given in this report, the decision rule is simple acceptance.

中国·浙江·海盐 盐北路211号 丰潭路777号 TEL: 0573-86161256 86161587

官网: <http://www.chinazbj.com>
Report check: <http://www.chinazbj.com>

检测报告

Test Report


报告编号/Report No. : 2020367120

页码/Page : 2/3

检测项目 /Test Item	检测方法 /Test Method	技术要求 /Requirement	检测结果 /Result	结论 /Conclusion
Fire resistance test	GB/T 9978.1-2008	—	升温至800℃，保温90min后，样品无明显变形，样品表面无裂纹 After heating to 800 °C and holding for 90 minutes, the sample has no obvious deformation and no cracks on the sample surface.	—


审核/Reviewed by :

章佳伟



耐火试验-测试前

Fire resistance test-Before testing




耐火试验-测试后

Fire resistance test-After testing

检测报告 Test Report

报告编号/Report No. : 2020367120

页码/Page : 3/3



耐火试验-时间温度曲线图
Fire resistance test-Time temperature curve

以下空白
REPORT FINALIZED